



## IIRCO CDD

*Copper dimethyl dithiocarbamate*  
**TTCu**

Product's Specification:

INDEX NAME		INDEX VALUE	
PHYSICAL PERFORMANCE	Appearance	Brown oil powder	Brown powder
	Melting point, °C, ≥	300.0	300.0
CHEMICAL PERFORMANCE	Loss on Drying, %, max	0.50	0.50
	Residues on 150 µm Sieve, max	0.10	0.10
	Residues on 63 µm Sieve, max	0.50	0.50
	Additive, %	0.1-1.0	/
	Ash content, %, max	0.50	0.50
	Tellurium Content, %	16.5-19.0	16.5-19.0

**Application:** Safe-processing secondary accelerator for use in black and dark colors. Fast at high vulcanization temperatures. Used in NR, SBR, IIR, NBR and EPDM. Better cure efficiency than IIRCO TMTD and IIRCO PZ. Lowest consumption in dithiocarbamates.

**Package:** 20kg plastic woven bag, paper with plastic film bag, Kraft paper bag.

**Storage:** The product should be stored in the dry and cooling place with good ventilation, avoiding exposure of the packaged product to direct sunlight. The validity is 1 year.

### IIRCO.

بازرگانی هاشمی

Tel: 021-22670733

تلفن: ۰۲۱-۲۲۶۷۰۷۳۳

021-22670832

۰۲۱-۲۲۶۷۰۸۳۲

Fax: 021-22209247

فاکس: ۰۲۱-۲۲۲۰۹۲۴۷

Email: IIRCO.TRADING@YAHOO.COM

IIRCO.TRADING@YAHOO.COM

ایمیل: