



IIRCO DPTT-4

dipentamethylene thiuram tetrasulphide

TRA-4

Product's Specification:

| INDEX NAME | | INDEX VALUE | | |
|----------------------|-------------------------------|----------------------|-------------------------|---------------------|
| PHYSICAL PERFORMANCE | Appearance | Light yellow granule | Light yellow oil powder | Light yellow powder |
| | Melting point, °C, ≥ | 108.0 | 108.0 | 108.0 |
| CHEMICAL PERFORMANCE | Loss on Drying, %, max | 0.30 | 0.50 | 0.30 |
| | Residues on 150 µm Sieve, max | / | 0.10 | 0.10 |
| | Residues on 63 µm Sieve, max | / | 0.50 | 0.50 |
| | Additive, % | / | 0.1-2.0 | / |
| | Ash content, % , max | 0.30 | 0.30 | 0.30 |
| | Granule diameter, mm | 1.50 | / | / |

Properties: Light yellow powder (granule-oil powder). No taste, no poison. The density is 1.5. Soluble in chloroform, benzene, acetone, CS₂, partly soluble in gasoline and CCl₄, insoluble in water and alkali of lower concentration.

Application: Secondary accelerator for NR, SBR, NBR and EPDM. For rich sulphur content of 28%, it could be used as cure agent. In the system of SBR and NBR, it could be used the primary cure agent. No poison and no pollution. Easily dispersed in rubber system.

Package: 25kg plastic woven bag, paper with plastic film bag, Kraft paper bag.

Storage: The product should be stored in the dry and cooling place with good ventilation, avoiding exposure of the packaged product to direct sunlight. The validity is 2 years.

IIRCO.

بازرگانی هاشمی

Tel: 021-22670733

تلفن: ۰۲۱-۲۲۶۷۰۷۳۳

021-22670832

۰۲۱-۲۲۶۷۰۸۳۲

Fax: 021-22209247

فاکس: ۰۲۱-۲۲۲۰۹۲۴۷

Email: IIRCO.TRADING@YAHOO.COM

IIRCO.TRADING@YAHOO.COM ایمیل: