## IIR CO.

**IIRCO ZDMC** Zinc dimethyl dithiocarbamate



Product's Specification:

PZ

INDEX NAME		INDEX VALUE		
PHYSICAL PERFORMANCE	Appearance	White granule	white oil crystal powder	white crystal powder
CHEMICAL PERFORMANCE	Melting point, $^{\circ}C$ , $\geq$	240.0	240.0	240.0
	Loss on Drying, $\%$ , $\leq$	0.30	0.50	0.30
	Residue on 150 $\mu$ m Sieve,%, $\leq$	/	0.10	0.10
	Residue on 63 µ m Sieve,%,≤	/	0.50	0.50
	Additive,%	/	0.1-2.0	1
	Zinc content,%	20.0-23.0	20.0-23.0	20.0-23.0
	Granule diameter, mm	2.50	/	/

**Properties:** White crystal powder (granule-oil crystal powder). No taste, no poison. The density is 1.66. Soluble in lower concentration alkali,  $CS_2$ , benzene, acetone and  $CH_2Cl_2$ , partly soluble in chloroform, insoluble in alcohol,  $CCl_4$  and ethyl acetate.

<b>Applications:</b>	Used for NR, IR, BR, SBR, NBR, HR, EPDM and natural & synthetic latexes. Stronger accelerating				
	power than IIRCO TMTD. Strong resistance to scorching. In its handling, care should be operated,				
	because of its increase activation and strong tendency to scorch at low temperatures (100°C). Often used				
	as a secondary accelerator. In latex, better results are obtained when used in combination with other types				
	such as thiazole accelerators. Used for rubber coated fabrics, latex products and rubber cement, etc. FDA				
	approved in USA.				
Package:	ge: 25kgs plastic woven bag, paper with plastic film bag, kraft paper bag.				
Storage <sup>.</sup>					

Storage: The product should be stored in the dry and cooling place with good ventilation, avoiding exposure of the packaged product to direct sunlight. The validity is 2 years.

بازرگانی هاشمی

Tel:	021-22670733	• T 1_T 7 F V • V M M	تلفن:
	021-22670832	• Y 1_Y Y 7 V • A W Y	
Fax:	021-22209247	· 7 1_777 · 974V	فاكس:
Email:	IIRCO.TRADING@YAHOO.COM	IIRCO.TRADING@YAHOO.COM	ايميل:

## IIRCO MADE IN CHINA, FOR INDUSTRIAL USE ONLY